

Grade/Product Name : 60505



Grade: HDPE & LLDPE Injection Moulding , Extrusion Coating & Rotomoulding

Test/Composition	value	Unit	Method
Break Strength	≥ 16	MPa	D 638
Density	960 ± 2	g/l	D 1505
Elongation at Break	200	%	D 639
Flexural Modulus	≥ 1480	MPa	D 790
HDT	≥ 78		D 1925
Izod 23°C	≥ 46	J/m	D 256/A
MFR "E"	5.5 ± 1	g/10 min	D 1238
Vicat	≥ 127	°C	D 1525
Yield Strength	≥ 30	MPa	D 638

Main Application: Crates

Product Type: HDPE Narrow MWD - Homopolymer Injection Moulding

Notes: Properties on compression moulded specimen according to method MA 17102, unless specified