

Grade/Product Name : 60507



Grade: HDPE & LLDPE Injection Molding , Extrusion Coating & Rotomoulding

Test/Composition	value	Unit	Method
Break Strength	13	MPa	D 638
Density	958	g/l	D 1505
Elongation at Break	350	%	D 639
Flexural Modulus	≥ 1500	MPa	D 790
Izod 23°C	≥ 36	J/m	D 256/A
MFR "E"	7.5 ± 1	g/10 min	D 1238
Vicat	≥ 127	°C	D 1525
Yield Strength	≥ 30	MPa	D 638

Main Application: Crates

Product Type: HDPE Narrow MWD - Homopolymer Injection Moulding

Notes: Properties on compression moulded specimen according to method MA 17102, unless specified