



TPC

Tabriz Petrochemical Company

Address :

**Azarshahr Road , Next
to the tabriz Refinery
Tabriz , Iran**

Po. BOX: 51745 - 354

Tel: [+98(0)411]4280000

FAX:

Tel: [+98(0)411]4201487

**LL0209 AA
Liner Low Density polyethylene**

- Product Description

- LL0209AA are linear low density polyethylene copolymers containing butane-1 as the co-monomer. In lean blends, this resin offer greater drawdown compared to LDPE neat and produced Films are tough with better tear resistance, high tensile stress and good hot-tack properties.

- Typical data

Property	Test Method	Unit	Typical Value
Physical Properties			
MFI(190°C/2.16Kg)	ASTM D 1238	gr/10Min	0.9
MFI(190°C/21.6Kg)			29.0
Density	ASTM D 1505	gr/cm ³	0.920
Optical Properties			
Haze	ASTM D 1003	%	12
Gloss(45°)	ASTM D 2457	%	50
Formulation			
Anti Oxidant			√
Anti Block			-
Slip Agent			-
Mechanical Properties			
Dart Drop Impact	ASTM D 1709(A)	g	140
Tear Strength MD/TD	ASTM D 1922	gr/25µm	145/370
Tensile Strength at yield MD/TD	ASTM D 882	MPa	10/11
Tensile Strength at Break MD/TD	ASTM D 882	MPa	41/32
Elongation at Break MD/ TD	ASTM D 882	%	620/840
Secant Modulus MD/ TD	ASTM D 882	MPa	195/205
Puncture Resistance	BPC	N.Cm	800
Coefficient of friction	ASTM D1894		> 0.5
Thermal Properties			
Vicat Softening Temperature	ASTM D 1525	°C	100

38µ , 2.5:1 blow-up ratio, 225°C melt temperature.

The above data are typical laboratory average. They are intended to serve as guide only.