



Tabriz Petrochemical Company

Address :

Azarshahr Road , Next
to the tabriz Refinery
Tabriz , Iran

Po. BOX: 51745 - 354

Tel: [+98(0)411]4280000

FAX:

Tel: [+98(0)411]4201487

LL 0220 KJ
Liner Low Density polyethylene

- Product Description

- LL0220KJ are linear low density polyethylene copolymers containing butane-1 as the comonomer. In lean blends, this resin offer greater drawdown compared to LDPE neat and produced Films are tough with better tear resistance, high tensile stress and good hot-tack properties. LL0220KJ offers high slip film with easy opening properties when used pure in thickness rang35-100µm. Addition of other polymers or use other thickness may alter film slip and antiblock performance.

- Typical data

Property	Test Method	Unit	Typical Value
Physical Properties			
MFI(190°C/ 2.16Kg)	ASTM D 1238	gr/10min	2.3
MFI(190°C / 21.6Kg)			-
Density	ASTM D 1505	gr/cm ³	0.920
Optical Properties			
Haze	ASTM D 1003	%	12
Gloss(45°)	ASTM D 2457	%	30
Formulation			
Anti Oxidant			√
Anti Block			√
Slip Agent			√
Mechanical Properties			
Dart Drop Impact	ASTM D 1709(A)	g	90
Tear Strength MD/TD	ASTM D 1922	gr/25µm	80/35
Tensile Strength at yield MD/TD	ASTM D 882	MPa	10/11
Tensile Strength at Break MD/TD	ASTM D 882	MPa	30/25
Elongation at Break MD/TD	ASTM D 882	%	1000/1100
Secant Modulus MD/TD	ASTM D 882	MPa	195/205
Puncture Resistance	BPC	N.Cm	800
Coefficient of friction	ASTM D1894		>0.5
Thermal Properties			
Vicat Softening Temperature	ASTM D 1525	°C	100

38µ , 2.5:1 blow-up ratio, 225°C melt temperature.

The above data are typical laboratory average. They are intended to serve as guide only.